

Short description of Material:

A partially crystalline thermoplastic with good toughness and high chemical resistance. PE-HMW has good sliding properties, but is only conditionally wear resistant and is suitable only for very lightly loaded sliding applications without high wear rates.

Application examples:

- cutting table liners
- impact bands
- knife blocks
- wall covers
- mixing spades

Colours: natural (white), green

Mechanical values

		dry	
Density	ISO 1183	0,95	g / cm ³
Yield stress	ISO 527	28	MPa
Elongation due to tearing	ISO 527	300	%
Modulus of elasticity resulting from tensile test	ISO 527	850	MPa
Modulus of elasticity resulting from bending test	ISO 178	850	MPa
Flexural strength	ISO 178	40	MPa
Impact strength ¹⁾	ISO 179	o.B.	kJ/m ²
Notched-bar impact strength	ISO 179	50	kJ/m ²
Ball indentation hardness H _{358/30}	ISO 2039-1	45	MPa
Creep rate stress at 1% elongation ²⁾	DIN 53 444	3	MPa
Sliding friction coefficient against steel (dry running) ³⁾	—	0,29	—
Sliding wear against steel (dry running) ³⁾	—	1,0	µm/km

Thermal values

Melting temperature	ISO 3146	+ 133	°C
Thermal conductivity	DIN 52 612	0,38	W/(K·m)
Specific thermal capacity	—	1,88	J/(g·K)
Coefficient of linear expansion ⁴⁾	—	18	10 ⁻⁵ ·K ⁻¹
Operating temperature range (long-term) ⁵⁾	—	- 100 / + 50	°C
Operating temperature range (short-term) ⁵⁾	—	+ 80	°C
Fire behaviour	UL 94	HB	—

Electrical values

Dielectric constant ⁶⁾	IEC 250	2,9	—
Dielectric loss factor ⁶⁾	IEC 250	0,0002	—
Specific volume resistance	IEC 93	> 10¹⁶	Ω·cm
Surface resistance	IEC 93	10¹⁴	Ω
Dielectric strength	IEC 243	44	KV/mm
Creep current resistance	IEC 112	KA 3c / KC >600	—

Miscellaneous data

Moisture absorption in normal climate until saturated	DIN 53 715	< 0,01	%
Water absorption until saturated	ISO 62	< 0,01	%

¹⁾: Measured with a pendulum impact testing machine 0,1 DIN 51 222

²⁾: Tension resulting in 1% total elongation after 1.000 h

³⁾: against steel, hardened and ground, P = 0,05 MPa, V = 0,6 m/s, t = 60 °C near running surface

⁴⁾: For a temperature range of + 23 °C to + 60 °C

⁵⁾: Experience values established with finished parts that are not under any stress in heated air, depending on the type and form of heat exposure, short-term = max. 1 h, long-term = months

⁶⁾: at 10⁶ Hz

w.b. = without breakage
 1 MPa = 1 N/mm²
 1 g/cm³ = 1.000 kg/m³
 1 kV/mm = 1 MV/m

Licharz GmbH

Industriepark Nord 15

D - 53567 Buchholz/Germany

Phone: ++49 / (0) 26 83 / 9 77 -0

Fax: ++49 / (0) 26 83 / 9 77 -111

Internet: www.licharz.de

E-Mail: info@licharz.de