

Short description of material

Amorphous high performance plastics with high strength and stiffness as well as good creep resistance over a wide temperature range. PEI also has a high long term operating temperature and good dimensional stability and is hydrolysis resistant.

Application examples

- Spools
- Sight glasses
- Gasket rings
- Equipment housing
- Insulating joints

Colours

Natural

Mechanical values

	ISO / EN / DIN	Dry	Humid	
Density	ISO 1183	1,27	--	g/cm ³
Yield stress	ISO 527	105	--	MPa
Elongation at break	ISO 527	>50	--	%
Modulus of elasticity from tensile test	ISO 527	3100	--	MPa
Modulus of elasticity from bending test	ISO 178	3300	--	MPa
Flexural Strength	ISO 178	145	--	MPa
Impact strength ¹⁾	ISO 179	without break	--	KJ/m ²
Notched-bar Impact Strength	ISO 179	--	--	KJ/m ²
Ball indentation hardness H358/30	ISO 2039-1	165	--	MPa
Creep rate stress at 1% Dehnung ²⁾	DIN EN ISO 899-1	--	--	MPa
Sliding friction coefficient against steel (dry running) ³⁾	-	--	--	-
Sliding wear against steel (dry running) ³⁾	-	--	--	µm/km

Thermal values

Melting temperature	ISO 3146	--	--	°C
Thermal conductivity	DIN EN 12939	0,22	--	W/(K*m)
Specific thermal capacity	-	--	--	J/(g*K)
Coefficient of thermal expansion (linear) ⁴⁾	-	5-6	--	10 ⁻⁵ *K ⁻¹
Operating temperature range (long-term) ⁵⁾	-	-40 bis +170	--	°C
Operating temperature range (short-term) ⁵⁾	-	+200	--	°C
Fire behaviour	UL 94, IEC 60695	V-0	--	-

Electrical values

Dielectric constant ⁶⁾	IEC 60250	3,0	--	-
Dielectric loss factor ⁶⁾	IEC 60250	0,003	--	-
Specific volume resistance	IEC 60093	10 ¹⁸	--	Ω *cm
Surface resistance	IEC 60093	10 ¹⁷	--	Ω
Dielectric strength	IEC 60243	33	--	kV/mm
Creep current resistance	IEC 60112	CTI 175	--	-

Miscellaneous data

Moisture absorption in normal climate until saturated	DIN EN ISO 62	0,75	--	%
Water absorption until saturated	DIN EN ISO 62	1,35	--	%

¹⁾ measured with a pendulum impact testing machine 0,1 DIN 51 222

²⁾ tension resulting in 1% total elongation after 1.000h

³⁾ against steel, hardened and ground

P = 0,05 Mpa; V = 0,6m/s; t = 60 °C near running surface

⁴⁾ For a temperature range of + 23 °C up to + 60 °C

⁵⁾ Experience values established with finished parts that are not under any stress in heated air, depending on the type and form of heat exposure, short-term = max. 1h, long-term=months

⁶⁾ at 10⁶ Hz

Licharz GmbH
 Industriepark Nord 13
 DE-53567 Buchholz
 phone: 0049-(0)2683-977-0
 e-Mail: info@licharz.com

The content of this datasheet are meant to give an overview of the product's properties. It reflects our current knowledge and may not be complete. The values should be taken as guide values because they are very depend on surrounding conditions and machining methods. The values are in no way a legally binding assurance of the product's properties or its suitability for use in a specific application. All stated values are average values established from many individual tests. They are based on a temperature of 23°C and 50% RH. For specific applications, we recommend determining suitability by means of a trial.